



ANCHOR SERVICE LIMITS *

MILD
STEEL




800°F

CAST
IRON




1000°F

DUCTILE
IRON




1095°F

304
SS




1650°F

309
SS




1850°F

310
SS




2050°F

330
SS



2100°F

CERAMIC
TILE



3000°F

* ANCHOR TIP TEMPERATURE
7/8/92